

**AMENDMENTS TO THE CLAIMS**

Claim 1 (Cancelled)

2. (Previously Presented) The composite sheet of claim 13, wherein the ultra fine fibers located on the surface of the composite sheet for artificial leather are raised.

Claim 3 (Cancelled)

4. (Previously Presented) The composite sheet of claim 13, wherein the yarn constituting the woven or knitted fabric layer is constructed of 200 to 10,000 ultra fine fibers.

5. (Previously Presented) The composite sheet of claim 13, wherein the total denier of the yarn constituting the woven or knitted fabric layer is 30 to 150 deniers.

6. (Previously Presented) The composite sheet of claim 13, wherein the number of twists of the yarn constituting the woven or knitted fabric layer is twisted to the extent of 500 to 700 twists/m.

7. (Previously Presented) The composite sheet of claim 13, wherein the number of twists of the yarn constituting the woven or knitted fabric layer is twisted to the extent of 700 to 2,500 twists/m.

8. (Previously Presented) The composite sheet of claim 13, wherein the yarn constituting the woven or knitted fabric layer is twisted to the extent of 2,500 to 4,000 twists/m.

9. (Previously Presented) The composite sheet of claim 13, wherein the yarn constituting the woven or knitted fabric layer is a staple spun yarn or continuous filament yarn.

10. (Previously Presented) The composite sheet of claim 13, wherein the yarn constituting the woven or knitted fabric layer is a polyester based resin or a nylon based resin.

11. (Currently Amended) The composite sheet of claim 13, wherein the weight of the woven or knitted fabric layer is 30 to ~~200g/M<sup>2</sup>~~ 200g/m<sup>2</sup>.

12. (Previously Presented) The composite sheet of claim 13, wherein the warp and weft densities of the woven or knitted fabric layer are more than 40 yarns/inch.

13. (Currently Amended) A composite sheet for artificial leather comprising:  
a non woven fabric layer made of ultra fine fibers;  
a woven or knitted fabric layer made of ultra fine fibers having a fineness of 0.01 to 0.3 denier; and  
polyurethane resin,

wherein the ultra fine fibers of the non woven fabric layer and the ultra fine fibers of the woven or knitted fabric layer are entangled with each other and the fineness of the ultra ~~'fine~~ fine fibers of the woven or knitted fabric layer is not more than the fineness of the ultra fine fibers of the non woven fabric layer.

14. (Original) The composite sheet of claim 13, wherein the ultra fine fibers located on the surface of the composite sheet for artificial leather are raised.

15. (Previously Presented) The composite sheet of claim 13, wherein the weight ratio of the non woven fabric layer to woven or knitted fabric layer is 90:10 to 50:50.

16. (Original) The composite sheet of claim 13, wherein the weight ratio of the ultra fine fibers to polyurethane resin is 90:10 to 50:50.

17. (Previously Presented) A composite sheet for artificial leather with low elongation and excellent softness, comprising:

a non woven fabric layer made of ultra fine fibers;

a woven or knitted fabric layer (2) made of ultra fine fibers having a fineness of 0.01 to 0.3 denier; and

polyurethane resin,

wherein the ultra fine fibers of the non woven fabric layer and the ultra fine fibers of the woven or knitted fabric layer are entangled with each other and the composite sheet has a stitching strength of more than 30kg/mm, an elongation at constant load of less than 20% and a stiffness of less than 80mm.

18. (Original) The composite sheet of claim 17, wherein the ultra fine fibers located on the surface of the composite sheet for artificial leather are raised.

19. (Currently Amended) The composite sheet of claim 13, wherein the ~~ultrafine~~ ultra fine fibers of the non-woven fabric layer have a fineness of less than 0.3 ~~denies-~~ denier.